

## SB-140 SKYLIGHT & WINDOW BUTYL SEALANT

**DESCRIPTION:** Flexible, one-part, easy-to-remove, elastomeric, butyl rubber sealant. Excellent for resealing and repairing leaks. USDA approved.

### USES:

#### Industries

- Construction
- Architectural
- Manufacturing
- RV Repair

#### Substrates

- Glass
- Metal
- Wood
- Concrete
- Cement
- Rubber materials (i.e. EPDM, TPO)
- Fiberglass
- Plastics
- Masonry

Not recommended for aquariums or terrariums, window glazing applications or hidden joint details (which require a non-skinning, non-hardening sealant).

**APPLICATION:** Interface and surfaces must be clean, dry and free of dust, dirt, oil and waterproofing and release agents. Protective coatings on glass and aluminum surfaces must be removed with solvents. Wood surfaces must be sanded and cleaned. Use standard cartridge gun. Approved tools dipped in water for troweling will ensure a complete filling of voids, as well as provide maximum contact with sealant. Press nozzle into groove and apply steady, even pressure to ensure that the joint is filled and no air is trapped.

**CLEANING:** While uncured, remove excess material from tools with naphtha or mineral spirits. See cautions on cleaner labels.

### FEATURES:

- Stays soft and malleable
- Flexible
- Excellent adhesion
- Fast-skinning
- Non-staining
- One-part
- Weather-resistant
- Paintable

### BENEFITS:

- Easy to remove
- Allows for movement of dissimilar materials
- Bonds to substrates without priming
- Minimizes dirt and dust pickup
- Will not discolor or rust material
- Easy application
- Long service life
- Easy to match substrate

**SHELF LIFE:** 12 months.

**STORAGE:** Unopened containers should be stored in an upright position in a cool, dry area. Rotate stock.

**CAUTION:** For industrial use only. Skin and eye irritant. Harmful if swallowed. Avoid contact with or breathing in of vapor and use adequate ventilation. Material on skin should be wiped and washed off with soap and water. For eyes, flush with water and seek medical attention. Keep away from open flames. SEE SAFETY DATA SHEET.

**PACKAGING:** 10.3 oz. tube

**COLOR:** White

### SPECIFICATIONS:

VOC	260 g/l	ASTM-D3960 Test Method
Tack-Free Time	2 Hours	ASTM-D2377 Test Method
Staining	None	
Solids	80%	
UV Resistance	No discoloration	
Application Temperature	40°F to 120°F	
Service Temperature	-20°F to 200°F	

All values are typical at 75°F, 50% R.H. unless otherwise noted.  
Federal Specifications TT-S-00230C used when applicable.

Revised: 9/25/15